



MATERIAL DATA

Magnetic Values		20°C	
Maximum Energy Product BH _(max)	Typ	KJ/m ³	262
	Min	KJ/m ³	247
Remanence Br	Typ	mT	1175
	Min		1140
Reversible temp coefficient of Br	Typ	-%/°C	0.08
Reversible temp coefficient of H _{cj}	Typ	-%/°C	0.45
Coercivity H _c	H _{cb} Typ	kA/m	900
	H _{cb} Min	kA/m	852
	H _{cj} Typ	kA/m	2786
	H _{cj} Min	kA/m	2786
Curie temperature	Min	°C	380
Max operating temp	Typ	°C	200
Magnetising field strength	Typ	kA/m	10000

Mechanical values		20°C	
Density	Typ	g/cm ³	7.50
Hardness	Typ	HV	500 - 520
Elasticity Modulus	Typ	10 ⁹ N/MM ²	135
Compressive Strength	Typ	N/mm ²	980
Flexural Strength	Typ	N/mm ²	260
Spec. Heat Capacity	Typ	J/(kg-K)	410
Thermal Conductivity	Typ	W/mK	7