



MATERIAL DATA

Magnetic values

			20°C
Maximum Energy Product	Typ	KJ/m ³	87.5
	Min	KJ/m ³	80
Remanence	Typ	mT	700
	Min		700
Reversible temp coefficient of Br	Typ	-%/°C	0.08
Coercivity	H _{cb} Typ	kA/m	400
	H _{cb} Min	kA/m	400
	H _{cj} Typ	kA/m	800
	H _{cj} Min	kA/m	800
Curie temperature	Min	°C	-
Max operating temp	Typ	°C	120
Magnetising field strength	Typ	kA/m	0

Mechanical values

			20°C
Density	Typ	g/cm ³	0.00
Hardness	Typ	HRB	0