



MATERIAL DATA

Magnetic values		20°C	
Maximum Energy Product	Typ	KJ/m ³	57.5
BH _(max)	Min	KJ/m ³	50
Remanence	Typ	mT	500
Br	Min	mT	500
Reversible temp coefficient of Br	Typ	-%/°C	0.08
Coercivity	H _{cb} Typ	kA/m	320
	H _{cb} Min	kA/m	320
	H _{cj} Typ	kA/m	800
	H _{cj} Min	kA/m	800
Curie temperature	Min	°C	-
Max operating temp	Typ	°C	120
Magnetising field strength	Typ	kA/m	0

Mechanical values		20°C	
Density	Typ	g/cm ³	0.00
Hardness	Typ	HRB	0