



MATERIAL DATA

Magnetic values		20°C	
Maximum Energy Product BH _(max)	Typ	KJ/m ³	135
	Min	KJ/m ³	127
Remanence Br	Typ	mT	875
	Min		850
Reversible temp coefficient of Br	Typ	-%/°C	0.042
Coercivity H _c	H _{cb} Typ	kA/m	634
	H _{cb} Min	kA/m	620
	H _{cj} Typ	kA/m	1353.5
	H _{cj} Min	kA/m	1194
Curie temperature	Min	°C	750
Max Operating Temp	Typ	°C	250
Magnetising field strength	Typ	kA/m	0

Mechanical values		20°C	
Density	Typ	g/cm ³	0.00
Hardness	Typ	HRB	0