



Magnetic values			20°C
Maximum Energy Product $BH_{(max)}$	Typ	KJ/m <sup>3</sup>	230
	Min	KJ/m <sup>3</sup>	220
Remanence Br	Typ	mT	1090
	Min		1080
Reversible temp coefficient of Br	Typ	-%/°C	0.032
Coercivity Hc	H <sub>cb</sub> Typ	kA/m	780
	H <sub>cb</sub> Min	kA/m	780
	H <sub>cj</sub> Typ	kA/m	1075
	H <sub>cj</sub> Min	kA/m	955
Curie temperature	Min	°C	800
Max operating temp	Typ	°C	300
Magnetising field strength	Typ	kA/m	0

Mechanical values			20°C
Density	Typ	g/cm <sup>3</sup>	8.30
Hardness	Typ	HRB	0