



Magnetic values

20°C

Maximum Energy Product	Typ	KJ/m ³	230
$BH_{(max)}$	Min	KJ/m ³	220
Remanence	Typ	mT	1115
B_r	Min		1080
Reversible temp coefficient of B_r	Typ	-%/°C	0.032
Coercivity H_c	H_{cb} Typ	kA/m	420
	H_{cb} Min	kA/m	420
	H_{cj} Typ	kA/m	480
	H_{cj} Min	kA/m	440
Curie temperature	Min	°C	800
Max operating temp	Typ	°C	300
Magnetising field strength	Typ	kA/m	0

Mechanical values

20°C

Density	Typ	g/cm ³	8.30
Hardness	Typ	HRB	0